


---

**Norm:** ASTM A475 - Standard Specification for Zinc-Coated Steel Wire Strand

---

**Applications & Usage:**

Galvanized steel strand used in electrical and distribution networks.

---

**Dimensional Characteristics**

Nominal Conductor Diameter	: 1" (25.40 mm)
Number of Strands	: 19
Nominal Diameter of Steel Strands:	: 0.200" (5.08 mm)
Approximate Weight	: 2,073 lb./1000 ft (3,089 kg/km)
Stranding Lay (unless otherwise specified)	: Left Lay

**Mechanical Characteristics**

**Common Grade**

Minimum Breaking Strength of Strand	: 28,700 lbf (127.664 kN)
Minimum Elongation (24" or 610 mm)	: 10%

**Siemens-Martin Grade (SM)**


Minimum Breaking Strength of Strand	: 47,000 lbf (209.066 kN)
Minimum Elongation (24" or 610 mm)	: 8%

**High Strength Grade (HS)**

Minimum Breaking Strength of Strand	: 73,200 lbf (325.610 kN)
Minimum Elongation (24" or 610 mm)	: 5%

**Extra High Strength Grade (EHS)**

Minimum Breaking Strength of Strand	: 104,500 lbf (464.839 kN)
Minimum Elongation (24" or 610 mm)	: 4%



---

### Galvanization Characteristics

Nominal Diameter of Steel Strands : 0.200" (5.08 mm)

Minimum Weight of Coating Zinc of Uncoated Wire Surface

- Class 1 - 0.40 oz/ft<sup>2</sup> (122 g/m<sup>2</sup>)
- Class A - 1.00 oz/ft<sup>2</sup> (305 g/m<sup>2</sup>)
- Class B - 2.00 oz/ft<sup>2</sup> (610 g/m<sup>2</sup>)
- Class C - 3.00 oz/ft<sup>2</sup> (915 g/m<sup>2</sup>)

### Packaging

Material & Type of Packaging : Heat-Treated Wooden Reels (HT 284 / ISPM-15)

Length of Cable per Reel : As requested by client