


---

**Norm:** ASTM A475 - Standard Specification for Zinc-Coated Steel Wire Strand

---

**Applications & Usage:**

Galvanized steel strand used in electrical and distribution networks.

---

**Dimensional Characteristics**

Nominal Conductor Diameter	: 7/8" (22.22 mm)
Number of Strands	: 19
Nominal Diameter of Steel Strands:	: 0.177" (4.50 mm)
Approximate Weight	: 1,581 lb./1000 ft (2,356 kg/km)
Stranding Lay (unless otherwise specified)	: Left Lay

**Mechanical Characteristics**

**Common Grade**

Minimum Breaking Strength of Strand	: 21,900 lbf (97.416 kN)
Minimum Elongation (24" or 610 mm)	: 10%

**Siemens-Martin Grade (SM)**

Minimum Breaking Strength of Strand	: 35,900 lbf (159.691 kN)
Minimum Elongation (24" or 610 mm)	: 8%

**High Strength Grade (HS)**


Minimum Breaking Strength of Strand	: 55,800 lbf (248.211 kN)
Minimum Elongation (24" or 610 mm)	: 5%

**Extra High Strength Grade (EHS)**

Minimum Breaking Strength of Strand	: 79,700 lbf (354.523 kN)
Minimum Elongation (24" or 610 mm)	: 4%



## Galvanized Steel Strand, 7/8" (19 Strands)



---

### Galvanization Characteristics

Nominal Diameter of Steel Strands : 0.177" (4.50 mm)

Minimum Weight of Coating Zinc of Uncoated Wire Surface

- Class 1 - 0.40 oz/ft<sup>2</sup> (122 g/m<sup>2</sup>)
- Class A - 0.90 oz/ft<sup>2</sup> (275 g/m<sup>2</sup>)
- Class B - 1.80 oz/ft<sup>2</sup> (549 g/m<sup>2</sup>)
- Class C - 2.70 oz/ft<sup>2</sup> (824 g/m<sup>2</sup>)

### Packaging

Material & Type of Packaging : Heat-Treated Wooden Reels (HT 284 / ISPM-15)

Length of Cable per Reel : As requested by client